

LGSO

Key Scintillator Materials for Novel Radiation Detectors


Features

- ✓ High Density and High Stopping Power
- ✓ Large Light Output and Superior Energy Resolution
- ✓ Short Decay Time
- ✓ No hygroscopicity




Applications

Positron Emission Tomography



Property



Comparison of Typical Scintillators

	LGSO	LSO	BGO	NaI:TI
Light output (NaI=100)	~90	~90	12	100
Decay time (ns)	40~42	40~42	300	230
Peak wavelength λ_{em} (nm)	410	410	480	415
Density (g/cm ³)	7.3~7.4	7.4	7.13	3.67
Effective atomic number Z_{eff}	63	63	77	50
Hygroscopicity	No	No	No	Yes
Self-radiation	Yes	Yes	No	No

OXIDE

OXIDE Corporation

1747-1 Maginohara, Mukawa, Hokuto, Yamanashi 408-0302 JAPAN
Tel: +81-551-26-0022, Fax: +81-551-26-0033



Sales@opt-oxide.com



<https://www.opt-oxide.com>



Oxide Yamanashi



OXIDE Corporation

Sales Contact in North America: Specialty Chemicals Dept., Marubeni America Corporation.
Tel: +1 (914) 428-8900, productinfo@marubeni.com